



04/30/2021

Newport
ASI # 58-011
7250 Reaume Road
Newport, MI 48166

2023-MDOT 23A

Procedure	Sieve/Test	Average	Unit	MDOT 23A
	1" (25mm)	100.0	%	100-100
	3/4" (19mm)	94.3	%	
	1/2" (12.5mm)	76.7	%	
	3/8" (9.5mm)	66.8	%	60-85
	#4 (4.75mm)	46.0	%	
	#8 (2.36mm)	32.2	%	25-60
	#16 (1.18mm)	23.6	%	
	#30 (.6mm)	18.7	%	
	#50 (.3mm)	15.4	%	
	#100 (.15mm)	13.6	%	
	#200 (75µm)	12.41	%	9-16
	Wash Loss (#200/75um)	12.0	%	9.0-16.0

Name/Title

Josh Orshoski / QC Tech