



04/30/2021

Newport  
ASI # 58-011  
7250 Reaume Road  
Newport, MI 48166

**2067-OH 467**

<b>Procedure</b>	<b>Sieve/Test</b>	<b>Average</b>	<b>Unit</b>	<b>467</b>
	1 1/2" (37.5mm)	100.0	%	95-100
	1" (25mm)	76.9	%	
	3/4" (19mm)	48.2	%	35-70
	1/2" (12.5mm)	24.3	%	
	3/8" (9.5mm)	15.8	%	10-30
	#4 (4.75mm)	4.2	%	0-5
	#8 (2.36mm)	2.6	%	
	Wash Loss (#200/75um)	1.5	%	0.0-2.0

**Name/Title**

Josh Orshoski / QC Tech