



04/30/2021

Newport
ASI # 58-011
7250 Reaume Road
Newport, MI 48166

2071-MFG. SAND

Procedure	Sieve/Test	Average	Unit	Man Sand- Gray
	3/8" (9.5mm)	100.0	%	85-100
	#4 (4.75mm)	95.6	%	
	#8 (2.36mm)	62.5	%	
	#16 (1.18mm)	36.8	%	
	#30 (.6mm)	21.7	%	
	#50 (.3mm)	11.5	%	
	#100 (.15mm)	7.3	%	
	#200 (75µm)	6.18	%	
	Wash Loss (#200/75um)	6.0	%	0.0-10.0

Name/Title

Josh Orshoski / QC Tech