

2072-Class II Limestone Sand

Procedure	Sieve/Test	Average	Unit	2072 Class II Limestone Sand
	3" (75mm)	100.0	%	100-100
	2 1/2" (63mm)	100.0	%	
	2" (50mm)	100.0	%	
	1 1/2" (37.5mm)	100.0	%	
	1" (25mm)	100.0	%	60-100
	3/4" (19mm)	100.0	%	
	1/2" (12.5mm)	100.0	%	
	3/8" (9.5mm)	100.0	%	
	#4 (4.75mm)	94.4	%	
	#8 (2.36mm)	60.7	%	
	#10 (2mm)	53.9	%	
	#16 (1.18mm)	35.8	%	
	#30 (.6mm)	21.3	%	
	#40 (.425mm)	15.6	%	
	#50 (.3mm)	11.6	%	
	#100 (.15mm)	7.4	%	0-30
	#200 (75µm)	6.17	%	0-7
	Wash Loss (#200/75um)	6.0	%	0.0-7.0
ASTM C70	Total Moisture	6.9	%	