



04/30/2021

Newport  
ASI # 58-011  
7250 Reaume Road  
Newport, MI 48166

### 2107-MI. 6AA Comm.

Procedure	Sieve/Test	Average	Unit	MI 6AA Comm.
	1 1/2" (37.5mm)	100.0	%	
	1" (25mm)	98.8	%	
	3/4" (19mm)	81.9	%	
	1/2" (12.5mm)	45.9	%	
	3/8" (9.5mm)	29.7	%	
	#4 (4.75mm)	8.1	%	
	#8 (2.36mm)	3.9	%	
	#16 (1.18mm)	1.2	%	
	Wash Loss (#200/75um)	1.8	%	

Name/Title

Josh Orshoski / QC Tech