



04/30/2021

Newport
ASI # 58-011
7250 Reaume Road
Newport, MI 48166

2121-MDOT 21AA Spec Limestone

Procedure	Sieve/Test	Average	Unit	MDOT 21AA Spec Limestone
	1 1/2" (37.5mm)	100.0	%	100-100
	1" (25mm)	92.6	%	85-100
	3/4" (19mm)	80.8	%	
	1/2" (12.5mm)	64.2	%	50-75
	3/8" (9.5mm)	55.2	%	
	#4 (4.75mm)	38.6	%	
	#8 (2.36mm)	26.2	%	20-45
	#16 (1.18mm)	18.4	%	
	#30 (.6mm)	13.8	%	
	#50 (.3mm)	10.6	%	
	#100 (.15mm)	9.0	%	
	#200 (75µm)	8.14	%	4-10
	Wash Loss (#200/75um)	7.8	%	4.0-10.0

Name/Title

Josh Orshoski / QC Tech