



04/30/2021

Ottawa Lake  
ASI # 58-003  
7555 Whiteford Rd  
Ottawa Lake, MI 49267

### 2004-OH 4 Limestone

Procedure	Sieve/Test	Average	Unit	ODOT 4
ASTM C136 and ASTM C117	2" (50mm)	100.0	%	100-100
	1 1/2" (37.5mm)	100.0	%	90-100
	1" (25mm)	52.2	%	20-55
	3/4" (19mm)	14.0	%	0-15
	1/2" (12.5mm)	2.2	%	
	3/8" (9.5mm)	1.5	%	0-5
	#4 (4.75mm)	1.3	%	
	Wash Loss (#200/75um)	0.9	%	

Name/Title

Josh Orshoski / QC Tech