



Ottawa Lake
 ASI # 58-003
 7555 Whiteford Rd
 Ottawa Lake, MI 49267

04/30/2021

All sampling and testing are performed in accordance with ASTM Section 4 Construction Volume 04.02 and MDOT Standard Specification for Construction 2012 Table 902-2 Section 703.

2006-MDOT 6AA Limestone

Procedure	Sieve/Test	Average	Unit	MDOT 6AA
ASTM C136 and ASTM C117	1 1/2" (37.5mm)	100.0	%	100-100
	1" (25mm)	99.9	%	95-100
	3/4" (19mm)	83.6	%	
	1/2" (12.5mm)	46.3	%	30-60
	3/8" (9.5mm)	25.7	%	
	#4 (4.75mm)	5.4	%	0-8
	#8 (2.36mm)	2.0	%	
	#16 (1.18mm)	1.5	%	
	#30 (.6mm)	1.3	%	
	#50 (.3mm)	1.2	%	
	#100 (.15mm)	1.1	%	
	#200 (75µm)	1.1	%	
	Wash Loss (#200/75µm)		1.0	%

All sampling and testing are performed in accordance with ASTM Section 4 Construction Volume 04.02 and MDOT Standard Specification for Construction 2012 Table 902-2 Section 703.

Name/Title

Josh Orshoski / QC Tech