



Ottawa Lake  
ASI # 58-003  
7555 Whiteford Rd  
Ottawa Lake, MI 49267

04/30/2021

All sampling and testing are performed in accordance with ASTM Section 4 Construction volume 04.02 and MDOT Standard Specification for Construction 2012.

### 2008-OH 8 Limestone

Procedure	Sieve/Test	Average	Unit	ODOT 8's
	1/2" (12.5mm)	100.0	%	100-100
	3/8" (9.5mm)	96.3	%	85-100
	#4 (4.75mm)	11.0	%	10-30
	#8 (2.36mm)	4.7	%	0-10
	#16 (1.18mm)	4.0	%	0-5
	#30 (.6mm)	3.6	%	
	#50 (.3mm)	3.2	%	
	#100 (.15mm)	3.1	%	
	#200 (75µm)	3.0	%	
	Wash Loss (#200/75µm)	2.7	%	

All sampling and testing are performed in accordance with ASTM Section 4 Construction volume 04.02 and MDOT Standard Specification for Construction 2012.

Name/Title

Josh Orshoski / QC Tech