



04/30/2021

Ottawa Lake
ASI # 58-003
7555 Whiteford Rd
Ottawa Lake, MI 49267

2010-Screenings

Procedure	Sieve/Test	Average	Unit	Screenings
	3/8" (9.5mm)	100.0	%	100-100
	#4 (4.75mm)	89.1	%	
	#8 (2.36mm)	54.7	%	
	#10 (2mm)	48.1	%	
	#16 (1.18mm)	34.0	%	
	#30 (.6mm)	23.9	%	
	#40 (.425mm)	20.9	%	
	#50 (.3mm)	18.6	%	
	#60 (.25mm)	17.5	%	
	#80 (.18mm)	17.1	%	
	#100 (.15mm)	15.8	%	
	#200 (75µm)	14.69	%	
	Wash Loss (#200/75um)	14.4	%	

Name/Title

Josh Orshoski / QC Tech