



Ottawa Lake
 ASI # 58-003
 7555 Whiteford Rd
 Ottawa Lake, MI 49267

04/30/2021

All sampling and testing are performed in accordance with ASTM Section 4 Construction volume 04.02 and MDOT Standard Specification for Construction 2012.

2017-MDOT 17A Limestone

Procedure	Sieve/Test	Average	Unit	MDOT 17A
ASTM C136 and ASTM C117	1" (25mm)	100.0	%	100-100
	3/4" (19mm)	92.6	%	90-100
	1/2" (12.5mm)	59.1	%	50-75
	3/8" (9.5mm)	36.3	%	
	#4 (4.75mm)	5.8	%	0-8
	#8 (2.36mm)	1.8	%	
	#16 (1.18mm)	1.3	%	
	#30 (.6mm)	1.1	%	
	#50 (.3mm)	1.0	%	
	#100 (.15mm)	0.9	%	
	#200 (75µm)	0.79	%	
Wash Loss (#200/75µm)		0.7	%	0.0-2.0

All sampling and testing are performed in accordance with ASTM Section 4 Construction volume 04.02 and MDOT Standard Specification for Construction 2012.

Name/Title

Josh Orshoski / QC Tech