



04/30/2021

Ottawa Lake
ASI # 58-003
7555 Whiteford Rd
Ottawa Lake, MI 49267

2021-MI 21AA COMM Limestone

Procedure	Sieve/Test	Average	Unit	OH 304
	1 1/2" (37.5mm)	100.0	%	100-100
	1" (25mm)	92.6	%	70-100
	3/4" (19mm)	82.1	%	50-90
	1/2" (12.5mm)	66.4	%	
	3/8" (9.5mm)	54.5	%	
	#4 (4.75mm)	38.0	%	30-60
	#8 (2.36mm)	24.9	%	
	#16 (1.18mm)	18.4	%	
	#30 (.6mm)	14.7	%	9-33
	#50 (.3mm)	12.6	%	
	#100 (.15mm)	11.4	%	
	#200 (75µm)	10.4	%	0-15
	Wash Loss (#200/75um)	10.1	%	0.0-15.0

Name/Title

Josh Orshoski / QC Tech