



Ottawa Lake
Pit # 58-003
7555 Whiteford Rd
Ottawa Lake, MI 49267
(734) 856-2257

01/09/2018

2022-MDOT 22A Limestone

Procedure	Sieve/Test	Average	Unit	MDOT 22A
	1" (25mm)	100.0	%	100-100
	3/4" (19mm)	95.9	%	90-100
	1/2" (12.5mm)	77.9	%	
	3/8" (9.5mm)	68.2	%	65-85
	#4 (4.75mm)	45.7	%	
	#8 (2.36mm)	30.4	%	30-50
	#16 (1.18mm)	19.0	%	
	#30 (0.6mm)	13.9	%	
	#50 (0.3mm)	11.0	%	
	#100 (0.15mm)	9.5	%	
	#200 (75µm)	8.7	%	4-10
	Wash Loss (#200/75um)	8.5	%	4-10