



04/30/2021

Ottawa Lake
ASI # 58-003
7555 Whiteford Rd
Ottawa Lake, MI 49267

2023-MDOT 23A Limestone

Procedure	Sieve/Test	Average	Unit	ODOT 617-411
	1" (25mm)	100.0	%	100-100
	3/4" (19mm)	95.8	%	60-100
	1/2" (12.5mm)	77.1	%	
	3/8" (9.5mm)	66.2	%	35-75
	#4 (4.75mm)	40.8	%	30-60
	#8 (2.36mm)	27.8	%	
	#16 (1.18mm)	19.7	%	
	#30 (.6mm)	16.3	%	9-33
	#50 (.3mm)	13.6	%	
	#100 (.15mm)	12.0	%	
	#200 (75µm)	11.2	%	0-15
	Wash Loss (#200/75um)	10.9	%	

Name/Title

Josh Orshoski / QC Tech