



04/30/2021

Ottawa Lake
 ASI # 58-003
 7555 Whiteford Rd
 Ottawa Lake, MI 49267

2029-MDOT 29A Limestone

Procedure	Sieve/Test	Average	Unit	MDOT 29A
	3/4" (19mm)	100.0	%	
	1/2" (12.5mm)	100.0	%	100-100
	3/8" (9.5mm)	94.7	%	90-100
	#4 (4.75mm)	20.4	%	10-30
	#8 (2.36mm)	4.8	%	0-10
	#16 (1.18mm)	3.6	%	
	#30 (.6mm)	3.1	%	
	#50 (.3mm)	2.8	%	
	#100 (.15mm)	2.7	%	
	#200 (75µm)	2.6	%	
	Wash Loss (#200/75um)	2.4	%	0.0-3.0

Name/Title

Josh Orshoski / QC Tech