



04/30/2021

Ottawa Lake  
ASI # 58-003  
7555 Whiteford Rd  
Ottawa Lake, MI 49267

### 2031-MDOT 31A Limestone

Procedure	Sieve/Test	Average	Unit	MDOT 31A
	1/2" (12.5mm)	100.0	%	100-100
	3/8" (9.5mm)	100.0	%	95-100
	#4 (4.75mm)	59.6	%	35-65
	#8 (2.36mm)	8.3	%	0-25
	#16 (1.18mm)	3.2	%	
	#30 (.6mm)	2.3	%	
	#50 (.3mm)	2.0	%	
	#100 (.15mm)	1.8	%	
	#200 (75µm)	1.7	%	
	Wash Loss (#200/75um)	1.6	%	0.0-3.0

Name/Title

Josh Orshoski / QC Tech