



04/30/2021

Ottawa Lake
 ASI # 58-003
 7555 Whiteford Rd
 Ottawa Lake, MI 49267

2071-MI MFG SAND Limestone

Procedure	Sieve/Test	Average	Unit	Top Stone /Finishing stone
	3/8" (9.5mm)	100.0	%	85-100
	1/4" (6.3mm)	100.0	%	75-100
	#4 (4.75mm)	95.1	%	60-90
	#8 (2.36mm)	54.9	%	35-75
	#16 (1.18mm)	27.1	%	10-55
	#30 (.6mm)	11.7	%	0-40
	#50 (.3mm)	4.4	%	
	#60 (.25mm)	3.2	%	0-15
	#100 (.15mm)	2.0	%	0-8
	#200 (75µm)	1.6	%	0-2
	Wash Loss (#200/75um)	1.5	%	0.0-2.0

Name/Title

Josh Orshoski / QC Tech