

2072-Class II Limestone Sand

Procedure	Sieve/Test	Average	Unit	2072-Class II Limestone Sand
	3" (75mm)	100.0	%	≤100
	1" (25mm)	100.0	%	60-100
	3/4" (19mm)	100.0	%	
	1/2" (12.5mm)	100.0	%	
	3/8" (9.5mm)	100.0	%	
	1/4" (6.3mm)	100.0	%	
	#4 (4.75mm)	95.2	%	
	#8 (2.36mm)	56.0	%	
	#10 (2mm)	48.0	%	
	#16 (1.18mm)	29.2	%	
	#30 (.6mm)	13.8	%	
	#40 (.425mm)	9.2	%	
	#50 (.3mm)	6.0	%	
	#60 (.25mm)	4.8	%	
	#80 (.18mm)	4.1	%	
	#100 (.15mm)	3.4	%	0-35
	#200 (75µm)	3.17	%	0-10
	Wash Loss (#200/75um)	2.8	%	0.0-10.0
ASTM C70	Total Moisture	5.2	%	