



04/30/2021

Ottawa Lake
ASI # 58-003
7555 Whiteford Rd
Ottawa Lake, MI 49267

2100-AG LIME Limestone

Procedure	Sieve/Test	Average	Unit	Ag Lime
	3/8" (9.5mm)	100.0	%	
	#4 (4.75mm)	99.4	%	
	#8 (2.36mm)	89.0	%	
	#10 (2mm)	84.4	%	
	#16 (1.18mm)	68.0	%	
	#30 (.6mm)	48.2	%	
	#40 (.425mm)	41.1	%	
	#50 (.3mm)	35.2	%	
	#60 (.25mm)	32.7	%	
	#100 (.15mm)	28.0	%	
	#200 (75µm)	25.0	%	
	Wash Loss (#200/75um)	24.4	%	

Name/Title

Josh Orshoski / QC Tech