



04/30/2021

Ottawa Lake
ASI # 58-003
7555 Whiteford Rd
Ottawa Lake, MI 49267

2107-MI. 6AA Comm. Limestone

Procedure	Sieve/Test	Average	Unit	MI 6AA Com.
	1 1/2" (37.5mm)	100.0	%	100-100
	1" (25mm)	100.0	%	
	3/4" (19mm)	87.6	%	
	1/2" (12.5mm)	45.5	%	
	3/8" (9.5mm)	21.0	%	
	#4 (4.75mm)	5.2	%	
	#8 (2.36mm)	2.5	%	
	Wash Loss (#200/75um)	1.0	%	

Name/Title

Josh Orshoski / QC Tech