



04/30/2021

Ottawa Lake
 ASI # 58-003
 7555 Whiteford Rd
 Ottawa Lake, MI 49267

2109-OH 9 WASHED Limestone

Procedure	Sieve/Test	Average	Unit	ODOT Mod. 9's
	3/8" (9.5mm)	100.0	%	100-100
	1/4" (6.3mm)	89.5	%	
	#4 (4.75mm)	52.6	%	45-60
	#8 (2.36mm)	10.9	%	0-30
	#16 (1.18mm)	3.9	%	
	#30 (.6mm)	2.6	%	
	#50 (.3mm)	2.2	%	
	#100 (.15mm)	2.0	%	
	#200 (75µm)	1.9	%	0-5
<hr/>				
	Wash Loss (#200/75um)	1.7	%	

Name/Title

Josh Orshoski / QC Tech