



04/30/2021

Ottawa Lake
 ASI # 58-003
 7555 Whiteford Rd
 Ottawa Lake, MI 49267

2121-MDOT 21AA Limestone

Procedure	Sieve/Test	Average	Unit	MDOT 21AA
	1 1/2" (37.5mm)	100.0	%	100-100
	1" (25mm)	88.8	%	85-100
	3/4" (19mm)	79.3	%	
	1/2" (12.5mm)	63.2	%	50-75
	3/8" (9.5mm)	57.2	%	
	#4 (4.75mm)	39.9	%	
	#8 (2.36mm)	28.1	%	20-45
	#16 (1.18mm)	20.0	%	
	#30 (.6mm)	15.1	%	
	#50 (.3mm)	12.4	%	
	#100 (.15mm)	10.9	%	
	#200 (75µm)	10.0	%	4-10
	Wash Loss (#200/75um)	9.7	%	4.0-10.0

Name/Title

Josh Orshoski / QC Tech