



Ottawa Lake
 Pit # 58-003
 7555 Whiteford Rd
 Ottawa Lake, MI 49267

07/12/2019

2023-MDOT 23A Limestone

Procedure	Sieve/Test	Average	Unit	MDOT 23A
	1" (25mm)	100.0	%	100-100
	3/4" (19mm)	96.6	%	
	1/2" (12.5mm)	79.5	%	
	3/8" (9.5mm)	67.2	%	60-85
	#4 (4.75mm)	43.0	%	
	#8 (2.36mm)	29.2	%	25-60
	#16 (1.18mm)	20.4	%	
	#30 (0.6mm)	16.2	%	
	#50 (0.3mm)	14.0	%	
	#100 (0.15mm)	12.6	%	
	#200 (75µm)	11.6	%	9-16
	Wash Loss (#200/75um)	11.4	%	9-16