



04/30/2021

Ottawa Lake  
ASI # 58-003  
7555 Whiteford Rd  
Ottawa Lake, MI 49267

### 2250-Mason Sand Natural

Procedure	Sieve/Test	Average	Unit
	3/8" (9.5mm)	100.0	%
	#4 (4.75mm)	99.7	%
	#8 (2.36mm)	96.6	%
	#16 (1.18mm)	91.2	%
	#30 (.6mm)	80.8	%
	#50 (.3mm)	49.6	%
	#100 (.15mm)	10.4	%
	#200 (75µm)	2.85	%
	Wash Loss (#200/75um)	2.5	%

Name/Title

Josh Orshoski / QC Tech