



04/12/2021

Patterson  
 ASI # 03-93  
 3700 Patterson Rd.  
 Middleville, MI 49333

**2021-MDOT 21AA**

Procedure	Sieve/Test	Average	Unit	MDOT 21AA Spec
	1 1/2" (37.5mm)	100.0	%	100-100
	1" (25mm)	100.0	%	85-100
	3/4" (19mm)	90.6	%	
	1/2" (12.5mm)	70.0	%	50-75
	3/8" (9.5mm)	59.8	%	
	#4 (4.75mm)	40.2	%	
	#8 (2.36mm)	30.0	%	20-45
	#16 (1.18mm)	25.1	%	
	#30 (.6mm)	22.1	%	
	#50 (.3mm)	14.3	%	
	#100 (.15mm)	7.6	%	
	#200 (75µm)	5.45	%	
	Fractured Faces (>1)	98.8	%	95.0-100.0
	-#200 (75um)	5.5	%	
	Wash Loss (#200/75um)	5.2	%	4.0-8.0
	Total Moisture	4.31	%	

**Name/Title**

Dan Ferris / QC