



04/12/2021

Patterson
 ASI # 03-93
 3700 Patterson Rd.
 Middleville, MI 49333

2222-MI 22A Gravel

Procedure	Sieve/Test	Average	Unit	MI 22A Gravel Spec
	1" (25mm)	100.0	%	100-100
	3/4" (19mm)	94.5	%	90-100
	1/2" (12.5mm)	84.1	%	
	3/8" (9.5mm)	77.2	%	65-85
	#4 (4.75mm)	60.6	%	
	#8 (2.36mm)	47.5	%	30-50
	#16 (1.18mm)	39.7	%	
	#30 (.6mm)	33.7	%	
	#50 (.3mm)	24.6	%	
	#100 (.15mm)	11.6	%	
	#200 (75µm)	7.89	%	
	Fractured Faces (>1)	54.8	%	25.0-100.0
	Wash Loss (#200/75um)	7.6	%	4.0-8.0

Name/Title

Dan Ferris / QC