



04/12/2021

Patterson
 ASI # 03-93
 3700 Patterson Rd.
 Middleville, MI 49333

2271-MI Class II Sand

Procedure	Sieve/Test	Average	Unit	MDOT Class II
	1" (25mm)	100.0	%	60-100
	3/4" (19mm)	100.0	%	
	1/2" (12.5mm)	100.0	%	
	3/8" (9.5mm)	99.9	%	
	#4 (4.75mm)	90.9	%	50-100
	#8 (2.36mm)	75.2	%	
	#16 (1.18mm)	65.9	%	
	#30 (.6mm)	57.8	%	
	#50 (.3mm)	27.5	%	
	#100 (.15mm)	6.8	%	0-30
	#200 (75µm)	4.19	%	
	-#200 (75um)	4.2	%	
	Wash Loss (#200/75um)	3.8	%	0.0-7.0
	Total Moisture	5.03	%	

Name/Title

Dan Ferris / QC