



04/12/2021

Patterson
ASI # 03-93
3700 Patterson Rd.
Middleville, MI 49333

2320-5/8 Wash

| Procedure | Sieve/Test | Average | Unit | 2021 Target |
|-----------|-----------------------|---------|------|-------------|
| | 3/4" (19mm) | 100.0 | % | 95-100 |
| | 1/2" (12.5mm) | 63.3 | % | 56-76 |
| | 3/8" (9.5mm) | 22.1 | % | 16-36 |
| | #4 (4.75mm) | 1.3 | % | |
| | #8 (2.36mm) | 1.1 | % | |
| | #16 (1.18mm) | 1.0 | % | |
| | #30 (.6mm) | 1.0 | % | |
| | #50 (.3mm) | 0.9 | % | |
| | #100 (.15mm) | 0.8 | % | |
| | #200 (75µm) | 0.79 | % | |
| | -#200 (75um) | 0.8 | % | |
| | Wash Loss (#200/75um) | 0.7 | % | |
| | Total Moisture | 1.40 | % | |

Name/Title

Dan Ferris / QC