



04/12/2021

Patterson
 ASI # 03-93
 3700 Patterson Rd.
 Middleville, MI 49333

2322-6A Gravel

Procedure	Sieve/Test	Average	Unit	6A Spec
	1 1/2" (37.5mm)	100.0	%	
	1" (25mm)	97.5	%	95-100
	3/4" (19mm)	75.5	%	
	1/2" (12.5mm)	41.0	%	30-60
	3/8" (9.5mm)	18.4	%	
	#4 (4.75mm)	2.1	%	0-8
	#8 (2.36mm)	1.0	%	
	#16 (1.18mm)	0.9	%	
	#30 (.6mm)	0.8	%	
	#50 (.3mm)	0.7	%	
	#100 (.15mm)	0.7	%	
	#200 (75µm)	0.58	%	
	-#200 (75um)	0.6	%	
	Wash Loss (#200/75um)	0.5	%	
	Total Moisture	2.16	%	

Name/Title

Dan Ferris / QC