



04/12/2021

Patterson
ASI # 03-93
3700 Patterson Rd.
Middleville, MI 49333

2348-20AA

Procedure	Sieve/Test	Average	Unit	20AA
	3/4" (19mm)	100.0	%	
	1/2" (12.5mm)	94.6	%	
	3/8" (9.5mm)	89.3	%	
	#4 (4.75mm)	74.2	%	
	#8 (2.36mm)	57.4	%	
	#16 (1.18mm)	47.3	%	
	#30 (.6mm)	39.3	%	
	#50 (.3mm)	20.4	%	
	#100 (.15mm)	6.9	%	
	#200 (75µm)	4.77	%	
	Fractured Faces (>1)	49.9	%	
	Wash Loss (63µm)	4.59	%	
	Total Moisture	4.56	%	

Name/Title

Dan Ferris / QC