



04/30/2021

Zeeb  
ASI # 81-92  
2575 South Zeeb Road  
Ann Arbor, MI 48103

### 2210-PEASTONE

Procedure	Sieve/Test	Average	Unit	Pea Stone
	3/4" (19mm)	100.0	%	100-100
	1/2" (12.5mm)	100.0	%	
	3/8" (9.5mm)	93.0	%	
	#4 (4.75mm)	10.6	%	
	#8 (2.36mm)	1.8	%	0-5
	#16 (1.18mm)	1.2	%	
	#30 (.6mm)	0.9	%	
	#50 (.3mm)	0.8	%	
	#100 (.15mm)	0.7	%	
	#200 (75µm)	0.61	%	
	Wash Loss (#200/75um)	0.6	%	

Name/Title

Josh Orshoski / QC Tech