



04/30/2021

Zeeb
 ASI # 81-92
 2575 South Zeeb Road
 Ann Arbor, MI 48103

2234-34R Gravel

Procedure	Sieve/Test	Average	Unit	34R
	1" (25mm)	100.0	%	100-100
	3/4" (19mm)	100.0	%	100-100
	1/2" (12.5mm)	100.0	%	100-100
	3/8" (9.5mm)	93.5	%	90-100
	#4 (4.75mm)	15.2	%	
	#8 (2.36mm)	3.6	%	0-5
	#16 (1.18mm)	2.0	%	
	#30 (.6mm)	1.6	%	
	#50 (.3mm)	1.4	%	
	#100 (.15mm)	1.3	%	
	#200 (75µm)	1.12	%	
	Wash Loss (#200/75um)	1.0	%	0.0-3.0

Name/Title

Josh Orshoski / QC Tech