



04/30/2021

Zeeb
ASI # 81-92
2575 South Zeeb Road
Ann Arbor, MI 48103

2272-2NS Sand

| Procedure | Sieve/Test | Average | Unit | MDOT 2NS |
|-----------|-----------------------|---------|------|----------|
| | 3/8" (9.5mm) | 100.0 | % | 100-100 |
| | #4 (4.75mm) | 95.9 | % | 95-100 |
| | #8 (2.36mm) | 75.3 | % | 65-95 |
| | #16 (1.18mm) | 43.4 | % | 35-75 |
| | #30 (.6mm) | 25.1 | % | 20-55 |
| | #50 (.3mm) | 11.2 | % | 10-30 |
| | #100 (.15mm) | 5.7 | % | 0-10 |
| | #200 (75µm) | 2.97 | % | |
| | Wash Loss (#200/75µm) | 2.7 | % | 0.0-3.0 |

Name/Title

Josh Orshoski / QC Tech