



04/30/2021

Zeeb  
 ASI # 81-92  
 2575 South Zeeb Road  
 Ann Arbor, MI 48103

**2370-Mfg Sand**

Procedure	Sieve/Test	Average	Unit	2370-Mfg Sand
	3/4" (19mm)	100.0	%	
	1/2" (12.5mm)	100.0	%	
	3/8" (9.5mm)	100.0	%	88-100
	#4 (4.75mm)	93.6	%	80-100
	#8 (2.36mm)	57.5	%	46-66
	#16 (1.18mm)	34.3	%	31-47
	#30 (.6mm)	21.1	%	20-36
	#50 (.3mm)	10.8	%	10-25
	#100 (.15mm)	4.1	%	2-8
	#200 (75µm)	2.48	%	0.5-5.5
	Wash Loss (#200/75um)	2.3	%	

**Name/Title**

Josh Orshoski / QC Tech